

# Technical data sheet

Date: January 26 2017

# Performance Brown SE

**BROWN SACK KRAFT PAPER** 

Production Unit: Skärblacka

#### End uses

Performance Brown SE is approved for sacks in accordance with the German norm for dangerous goods. This grade is therefore recommended for sacks in the cement and chemical industries, where demands are rigorous.

## Grammages

70-90 g/m<sup>2</sup>

## Materials

Performance Brown SE is produced from pure, unbleached kraft pulp and consists entirely of virgin fibres. The long and strong fibres, from Nordic slowly growing softwood forests, give the paper its inherent strength.

#### **Approvals**

Performance Brown SE is produced in compliance with FDA and BfR food packaging norms.

## Certification

Skärblacka mill is certified in accordance with ISO 9001, ISO 14001 and ISO 50001.

Property	Unit		Typical values				Method
Grammage	g/m <sup>2</sup>		70	80	85	90	ISO 536
Tensile strength	kN/m	MD	5.6	6.4	6.8	7.2	ISO 1924-3
	kN/m	CD	4.9	5.6	6.0	6.3	
Tensile index	Nm/g	MD	80	80	80	80	ISO 1924-3
	Nm/g	CD	70	70	70	70	
Stretch	%	MD	6.0	6.0	6.0	6.0	ISO 1924-3
	%	CD	8.0	7.7	7.7	7.5	
TEA	J/m <sup>2</sup>	MD	210	240	255	260	ISO 1924-3
	J/m <sup>2</sup>	CD	220	250	255	270	
TEA Index	J/g	MD	3.0	3.0	3.0	2.9	ISO 1924-3
	J/g	CD	3.1	3.1	3.0	3.0	
TEA index geometric	J/g		3.1	3.1	3.0	3.0	
Tear strength	mN	MD	910	1040	1105	1170	ISO 1974
	mN	CD	910	1040	1105	1170	
Tear index	mNm²/g	MD	13	13	13	13	ISO 1974
	mNm²/g	CD	13	13	13	13	
Cobb 60s	g/m <sup>2</sup>	WS	28	28	28	28	ISO 535
Air resistance	S		10	10	10	10	ISO 5636-5
Friction coeff. Static			0.65	0.65	0.65	0.65	ISO 15359
Moisture	%		7.0	7.0	7.0	7.0	ISO 287

MD = Machine Direction CD = Cross Direction WS = Wire Side

Test climate: 50% RH, 23°C